

Stoner Molding Solutions®
You Mold It. We Release It.®

TraSys® 9825

Water Based Mold Release Agent



Product Description

TraSys® 9825 mold release coating is a water-based dispersion for hot mold applications. When applied to a mold, it exhibits outstanding durability and antistick properties and has a very low coefficient of friction. It is clean, non-oily, non-staining, chemically inert, and can function in high temperatures.

TraSys® 9825 mold release coating has unique properties, making it an excellent release agent for molded rubber, molded fluoropolymer, molded plastic, and epoxy and plastic laminates. Unlike oily release agents, when properly applied, it does not interfere with post-finishing operations.

TraSys® 9825 comes pre-diluted and is ready for use. Proper application results in superior release, and multiple releases are normal.

Uses

TraSys® 9825 is ideal for compression, transfer, and injection molding of most rubber compounds and thermoset resins.

Directions for Use

TraSys® 9825 must be agitated before spraying. TraSys® 9825 mold release coating should be sprayed on hot, clean, and dry surfaces. For maximum results, preheat the mold surface to 87-149°C (190-300°F) before application. Properly applied, the coating will not be affected by water or most other materials that may come in contact with it.

Recommended Procedure

1. Clean mold thoroughly, using glass or plastic bead media, abra- sive pads, and cleaning solvent or high pH detergent, to remove all prior mold release and other sources of contamination.

2. Use low pressure spray equipment that provides a fine mist. After agitation, apply lightly to a hot mold, making certain that all areas of the mold are entirely coated.
3. Although it is not necessary to bake TraSys® 9825, in some cases increased performance has been achieved by baking Tra- Sys® 9825 onto the mold's surface for 5 min at normal operating temperature (a minimum of 132°C [270°F]).

When spot touch-ups are applied, curing the freshly coated area with a heat gun will further enhance the bond between the coating and the mold's surface. Larger applications may require a bake cycle as described above. This will give a bond between mold and coating that will ensure the most effective coating for durability and cycle life.

Storage and Handling

TraSys® 9825 should be stored in a cool, dry, well ventilated area. Do not expose to freezing temperatures. Freezing will affect the physical condition, but will not damage the release effectiveness. Thaw at room temperature, and mix well before using.

Containers in use should be agitated before use and often during use. Drums will require a low rpm agitator to prevent phase separation in the storage container.

Breathing vapors should be avoided. If spraying, care should be taken to avoid inhaling mist or vapors, just as sprayed paint inhalation should be avoided.

Care should be taken not to expose TraSys® 9825 mold release coating to open flame or intense heat. Temperatures above 260°C (500°F) may cause chemical breakdown, resulting in toxic fumes. Always wash hands after handling TraSys® 9825 mold release coating.

Shelf Life

TraSys® 9825 has a shelf life of up to 2 years from the date of manufacture printed on the container label.

Packaging

TraSys® 9825 is available in:

- Cases of 4x1-gallon Part # TRA9825GLXX2
- 5-gallon pails Part # TRA9825PLXX2
- 55-gallon drum Part # TRA9825DRXX1

Technical Assistance

Call: 800-227-5538 or 1 (717) 786-7355
Email: CustomerService@StonerMolding.com
Visit: StonerMolding.com

NO RISK GUARANTEE. Stoner Molding guarantees 100% satisfaction or your money back. If you're ever dissatisfied with any Stoner Molding product, simply return the unused portion for a full refund.



StonerMolding.com

1070 Robert Fulton Hwy. • Quarryville, PA 17566 • 1-800-227-5538 • 1-717-786-7355

Made
in USA